



BLENDING FLASH

Blending thinner

C 5

Product description







Smooths transition areas from blend-in zones to old paintwork.

Technical characteristics

Shelf life: 24 months Density: 0.909 g/cm³ Theoretical spreading rate: m²/l at 1 µm
Colour: transparent Solids content: 1.3 % by weight

Pre-treatment

See BLEND'ART processes.

	Mixing ratio	The product is ready for use.
	Spray viscosity	17 seconds ISO 4 cup at 20°C
	Potlife	N/A
	Sprayguns	HVLP minijet gun 1.0 – 1.2 0.5 – 0.7 bar at the nozzle
	Application	2 – 3 spraycoats to the clear fade-out areas to smooth them.
	Drying	As recommended for the R-M clear used.
	Further treatment	If necessary, minor defects can be polished out with FINE BRIL once the clear coat has fully cured.

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules. The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.