



SPEEDFLASH

Additive to accelerate drying

C 5

Product description





Additive used to reduce the drying times of R-M 2-component standard VOC clear coats (CRYSTALCLEAR CP, STARLUX CP, CHRONOLUX CP, DIAMONTCLEAR CP) on vertical surfaces. SPEEDFLASH increases the chemical reactivity of the products in which it is used, allowing shorter waiting times before sanding, polishing operations or reassembly can be started. The amount of SPEEDFLASH to be added corresponds with the amount of thinner indicated in the standard mixing ratio.

Technical characteristics

Shelf life: 24 months Density: 0,875 g/cm³ Theoretical spreading rate: / m²/l at 1 µm
Colour: transparent Solids content: 0,4 % by weight

Pre-treatment

As specified in the technical data sheet of the product in which SPEEDFLASH is being used.

	Mixing ratio	R-M VOC Standard clearcoat 300 (vol.) H 420 100 (vol.) SPEEDFLASH 100 (vol.)
	Potlife	Mix well and strain before application. The use of SPEEDFLASH will reduce the potlife of the products.
	Sprayguns	As specified in the technical data sheet of the product in which SPEEDFLASH is being used.
	Application	As specified in the technical data sheet of the product in which SPEEDFLASH is being used.
	Drying	Drying at 60°C: CHRONOLUX CP 10 min. CRYSTALCLEAR CP 25 min. DIAMONTCLEAR CP 25 min. STARLUX CP 25 min.

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules. The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.