



SUPREMECLEAR

Scratch-resistant clear

C 4

Product description









Clear for repairing vehicles with scratch-resistant original paint finishes.

Technical characteristics

Shelf life:	36 months	Density:	0.986 g/cm ³	Theoretical spreading rate:	237 m ² /l at 1 µm
Colour:	transparent	Solids content:	48.0 % by weight		

Pre-treatment

SUPREMECLEAR was designed for use on DIAMONT and ONYX HD basecoats.

	Mixing ratio	SUPREMECLEAR 100 (vol.) 100 g H 9000 25 (vol.) 27 g SC 850 25 (vol.) 22 g
Mix well and strain before application. Note: Use the slower SC 880 thinner in temperatures above 25°C or when refinishing large surfaces.		
	Spray viscosity	28 to 32 seconds ISO 4 cup at 20°C
	Potlife	4 hours at 20°C
	Sprayguns	HVLP gravity-feed spraygun 1.3 – 1.5 0.7 bar at the nozzle Compliant gravity-feed spraygun 1.3 – 1.4 2.0 – 2.5 bar
	Application	Number of spraycoats: 2 Film thickness: 60 µm
	Drying	Drying at 60°C: 30 min.
	Infrared drying	(short wave) 8 min. (medium wave)
	Further treatment	Finishing operations after specified drying times and cooling

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules. The products are suitable for professional use only.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. It cannot be ruled out that this product contains particles < 0.1 µm.