

PRODUCT DATA SHEET

PK 300W



Application

PK 300W wipes are intended for use on cleaned bare metal surfaces such as steel, galvanized steel and aluminum.



Description:

Thanks to their chemical reaction in contact with metal surfaces, PK 300W wipes increase the corrosion resistance and adhesion of the paint system to be applied.

Substrates:

- = very well suited
- = well suited
- = suited in some cases

Steel	●●
Galv. Steel	●●
Stainless steel	●●
Aluminium	●●
Anodized Aluminium	●
GRP / SMC	
PP-EPDM	
RM CV-Primer	
RM CV-Primer-Filler / Filler	
Powder	
Coil-Coating	
Plywood	
Wood	
OEM Paint work	
Old paint work	

Special remarks

- Recoatable with all R-M CV undercoats, except polyester body filler
- If you want to reuse used wipes during the same working day, store them in a container or in a resealable plastic bag. This will protect the wipes from drying out. Do not return used wipes to the original packaging.
- **2004/42/II B(c)(780)8:** The EU limit value for this product (product category: IIB.c) in ready-for-use form is max 780 grams of VOC per liter. The VOC content of this product is 8 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, BASF Coatings S.A.S, F-60676 Clermont-de-l'Oise Cedex

Oct. 2014

Perfection made simple



PRODUCT DATA SHEET

PK 300W



Paint system



Observe process-related regulations. Use on cleaned bare metal surfaces only.

Spreading rate

per cloth max 3m²

Close container



Close the container immediately after removing an PK 300W. Wipe to protect the other wipers from drying out.

Cleaning



PK 1000 / 2000 (see relevant refinishing system)

Application



Evenly wet the entire bare metal surface with PK 300W.
(Wipe with overlapping single cross coats).

The surface must stay moist for at least 1 minute. This is imperative for the chemical reaction to complete and form a passivation layer.

Flash-off at 20°C



Matt surface, approx. 15 min.

Max. 8 h

Paint system

Can be overcoated with all R-M CV undercoats, see technical data sheet or refinishing systems

It is not recommended to use PK 300W wipers on aluminum interlocking profiles and large surfaces, because a homogeneous application can't be guaranteed.