

PRODUCT DATA SHEET

STOP MULTI

white

BF

Application

all applications



Description:

- fast drying
- suitable on all substrates
- good filling properties
- fast sandable

Substrates:

- = very well suited
- = well suited
- = suited in some cases

| | |
|------------------------------|----|
| Steel | ●● |
| Galv. Steel | ●● |
| Stainless steel | ○ |
| Aluminium | ●● |
| Anodized Aluminium | ●● |
| GRP / SMC | ● |
| PP-EPDM | ●● |
| RM CV-Primer | ●● |
| RM CV-Primer-Filler / Filler | ● |
| Powder | ● |
| Coil-Coating | ● |
| Plywood | ● |
| Wood | ● |
| OEM Paint work | ● |
| Old paint work | ● |

Remarks:

The substrate should be clean, free of dust, rust, oil and grease

Special remarks

- The products are suitable for professional use only.
- It cannot be ruled out that this product contains particles < 0.1 µm
- **2004/42/IIIB (b)(250)180:** The EU limit value for this product (product category: IIB(d) in ready to use form is max.. 250 g/l. **The VOC content of this product is 180 g/l.**



Paint process

Can be used for all CV Painting Processes.

Spreading rate

Solid content

98 %

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, BASF Coatings S.A.S, F-60676 Clermont-de-l'Oise Cedex

Jan 2014

Perfection made simple



PRODUCT DATA SHEET

STOP MULTI

white

BF



Mixing ratio 100:2-3 by weight

Hardener STOP HARDENER

Reducer

Spray viscosity
DIN 4 / 20°C

Potlife 20 °C

4 min



Drying



over-coatable



tack free



tapeable



ready to assemble



sandable

Min. Max.

Panel temperat. 20°C

20-30 min

Panel temperat. 60°C

Remarks



Can be sanded after 20-30 min
Not suitable for applications that require elasticity, e.g., weld seams.
Do not apply on etch wash primer or acid pre treated substrates!